

# TECHNICAL DATA

# Scapa 3120

Waterproof Cloth Tape

## DESCRIPTION

Scapa 3120 is a medium performance, strong, polyethylene coated 70mesh, waterproof cloth tape, coated with a pressure sensitive adhesive.

Scapa 3120 is available in a full range of colours including black, white, silver, red, yellow, blue and green.

# APPLICATIONS

- Duct sealing covering joints in hot air and insulating material
- Fixing and holding of wires and cables, especially on film sets
- Heavy duty and export packaging for drum sealing and colour coding
- Double glazing unit sealing
- Masking applications
- Carpet joining and edging
- Colour coding and identification
- Joining and splicing applications
- Ideal for general purpose applications where added strength and performance required

## **PRODUCT BENEFITS**

- Excellent waterproof properties
- Good strength
- Highly flexible and conformable
- Good initial tack and ultimate adhesion
- Good unwind
- Easy tear
- Peels off easily after use
- Low and high temperature performance
- Good all round performance Service Temperature -20 to 80°C

#### Issue : 6

Date : 01.02.12

Page 1 of 2

3120.doc

#### www.scapa.com

The information supplied is accurate to the best of Scapa's knowledge and is based upon all current data available to it. Properties quoted are typical and do not therefore constitute a specification. Customers must complete their own assessment of the product for its intended application under their own conditions. Our technical advice is to be regarded as an expression of opinion only and although such advice is given in good faith, it shall not, in any circumstances, be regarded as the basis of or as being a representation or statement of fact. This applies also where propriety or protective rights of third parties are involved. Any liability arising in respect of our products will be strictly limited to the value of those products charged to the customer and shall not extend to any consequential loss whatsoever and howsoever arising. Freedom from Patent Rights must not be assumed. This document does not form part of any contract with a customer.

## TECHNICAL PROPERTIES

	Unit	Nominal Value	Test Method
Thickness	mm	0.2 <b>6</b>	AFERA 5006*
Tensile Strength	N/cm	48	IEC 454-2
Adhesion to Steel	N/cm	4	IEC 454-2
Adhesion to Backing	N/cm	2.5	IEC 454-2

\* Scapa Internal Test Method to measure thickness now replaced by the more rigorous AFERA method.

### STANDARD PRESENTATION

Roll Length:	25m, 50m
Roll Width:	19mm, 25mm, 38mm, 50mm, 75mm, 100mm
Core:	Cardboard
Packaging:	Bulk packed using interleaving sheets between layers
1	a start it is a start start start start start in a time a time a start start is start at the start start start

Note: Information on stock items, non standard sizes and lead times is available on request

### RECOMMENDATIONS

I ne rolls should be stored flat on their cut edges in the original packaging, until required for use.

The product must be protected from dust, heat, moisture, direct sunlight and solvent fumes. helf life will vary with conditions of use and is affected by climatic environment, but should not be less than

two years from date of manufacture, if stored in a moderate climate and good conditions.

Issue: 6 www.scapa.com Date : 01.02.12

Page 2 of 2

The information supplied is accurate to the best of Scapa's knowledge and is based upon all current data available to it. Properties quoted are typical and do not therefore constitute a specification. Customers must complete their own assessment of the product for its intended application under their own conditions. Our technical advice is to be regarded as an expression of opinion only and although such advice is given in good faith, it shall not, in any circumstances, be regarded as the basis of or as being a representation or statement of fact. This applies also where propriety or protective rights of third parties are involved. Any liability arising in respect of our products will be strictly limited to the value of those products charged to the customer and shall not extend to any consequential loss whatsoever and howsoever arising. Freedom from Patent Rights must not be assumed. This document does not form part of any contract with a customer.